

# Technailcolor mixable colored acrylic

## Nail Enhancement Instructions

For Professional Use Only



Technailcolor Mixable Colored Acrylic – High pigment colours that can be mixed for endless design possibilities. Delivers exceptional adhesion, strength, and flexibility when used with Attraction Nail Liquid. Iridescent super-fine glitter can be mixed with any acrylic powder or gel for added dimension.

Made in the USA by NSI. W. Conshohocken, PA 19428 USA  
Tel: 800.354.6741 • 610.825.1524 • Fax: 610.825.2738  
**BIORIUS, RUE DE LA CROYERE 10A, BE-7170 MANAGE**

### MIX RATIO

**Attraction Nail Liquid should be worked in a medium wet mix ratio.**

1. Submerge brush completely into your *Dappen Dish* containing desired monomer, and flatten hairs to saturate brush. This will prevent dry powder and will force out any oxygen trapped around the brush hairs. Complete saturation is recommended at the beginning of each service.
2. Wipe the brush along the sides of the moistened dish to release excess liquid. This pressure will also create a flat side to the brush. The more liquid you remove, the smaller bead pick up you'll have, while still maintaining a medium wet mix. Leave larger amounts of liquids for larger beads that may be required.
3. Dip the flags (the very tip of the brush) into the powder. Gently drag and press the brush into the powder.
4. When the bead is on the brush, wait until all the powder is absorbed and looks like a smooth pearl. The bead should be medium wet, looking slightly frosted and dimpled with no loose powder. When the bead is placed on the nail, it should level about 25 percent. It should move where you want it without running or being unable to press. Use your eyes to see that the colour looks correct, and your touch to determine the feel of the bead.

### NATURAL NAIL PREP

1. Spray your hands and clients' hands with *Purify*. Push back the cuticle and gently remove shine with a *Endurance 180/240 Grit Buffer*. Using a *Nail Wipe* saturated with *Nailpure Plus*. Press and rub into natural nail.
2. If extensions are desired, adhere tip or fit a nail form at this time.
3. Apply *Attract (Acid-Free) Primer* liberally to the natural nails. Remove the brush from the bottle and wipe along the edge of the bottle, then brush onto the natural nail. Re-dip the brush and repeat the process until the nails are coated. Allow to dry for one minute. They will not appear chalky white.

### Zone 1 - The Extension Edge

Using the Technailcolor Powder of your choice

1. Using a medium-wet mix, place the bead in the middle of Zone 1; The front of the bead is the highest point of your smile line. Give the bead a few seconds to begin leveling. Using the tip of the brush, lightly press from side to side to evenly distribute the product. As you lightly press, start pushing and guiding the product up into the corners to form the smile line. The smile line should be slightly past the free edge line. Smooth down over the entire extension edge. Remember to use a light touch when you first start pressing down the bead. As the product starts to harden, press more firmly.
2. Wipe off any excess from the brush onto a clean towel and taper the brush into a point. While the product is still pliable, back brush the smile line to make it crisp and clean.

**NOTE: Choose the desired Technailcolor Powder or any colour Attraction Powder mixed with approximately 25% Opal Shimmer. When mixing Opal Shimmer directly into acrylic powder, you must always use a ratio of 25% Opal Shimmer or less. This will assure proper polymerization of the product.**

### Zone 2 - The Stress Area

1. Place a bead of powder just slightly beyond Zone 1, without overlapping or touching the bead in Zone 1. Press gently from side to side to coat the nail evenly.
2. Pat and squeeze the bead to the side edge of the nail angling your brush to mirror the contours of the nail. Stroke the rest of the product towards the center including over Zone 1. This starts to build the apex

### Zone 3 - The Cuticle Area

1. Place another bead in Zone 3 near the product in Zone 2. Angle your brush and thin the front of the bead so it leaves a tiny margin around the cuticle and side walls. This will assure that you are not overexposing your clients' nail.
2. If additional product is needed to create the apex, use a small bead of clear powder in Zone 2. Allow the product to set, until you hear a click.

**NOTE: If you are using multiple Technailcolors in thin layers, you must overlay the entire enhancement in Attraction Totally Clear Powder prior to filing. You risk filing away the nail art design if this step is missed.**

### FINISHING THE NAIL

1. Using an *Endurance 180/180 Grit File*, define the shape. Start with the side walls. Make sure they are parallel and not fanning out. File free edge into the desired shape. Refine surface and check for proper design and apex placement. File the nail so it is smooth, balanced and attractive following the curvature of the nail.
2. Remove excess dust with your *Plush Brush*. Use a *Nail Wipe* lightly saturated with *Cleanse* to remove any dust that may be hiding in the side walls.
3. Either buff to a high shine or apply *Glaze 'n Go LED* following the directions on the packaging. Condition the cuticle and surrounding skin with *Nurture Oil*.

### REMOVAL

1. Remove the shiny shield of the top coat with an *Endurance 180/180 Grit File*.
2. Place the tips of the fingers into a bowl of *Soothing Soak Off Remover*. This will keep your clients' hands nourished and pampered during removal.
3. Continue to file and soak until product is completely removed. The product will go frilly around the edges of the enhancement. When ready it will be soft. Use an orange stick or equivalent tool to peel off the remaining product.
4. At this time your nails are ready for reapplication of product or wash hands with warm water and soap and condition with *Nurture Oil*.

**INGREDIENTS:** Polyethylmethacrylate, Polymethylmethacrylate, Benzoyl Peroxide, Silica. May Contain (+/-): Orange 5 (CI 45370), Red 30 (CI 73360), Red 7 (CI 15850), Blue 1 (CI 142090), Iron Oxides (CI 77489), Maganese Violet (CI 77742), Mica, Red 6 (CI 15850), Red 21 (CI 45380), Red 27 (CI 45410), Red 40 (CI 16035), Iron Oxides (CI 77491), Titanium Dioxide (CI 77891), Violet 2 (CI 60725), Yellow 10 (CI 47005), Yellow 5 (CI 19140), Iron Oxides (CI 77492).

**WARNING: For Professional Use Only.** Avoid skin and eye contact or inhalation. External use only. For emergency medical information, contact Infotrac Chemical Emergency Response at 1-800-535-5053. If outside the U.S., contact your local Poison Control Center.