

nsi  
*Balance*  
 LED/UV GEL SYSTEM  
 PolyPaste

**INSTRUCTIONS:**

**Balance LED/UV PolyPaste System** - a light cured gel-hybrid system. PolyPaste can be used for sculpting an extension or adding a layer of protection, the PolyPaste is the newest way to build an enhancement. Great for techs looking to expand into gel, but shy away from traditional hard gels.

Made in the USA by NSI. W. Conshohocken, PA 19428 USA  
 Tel: 800.354.6741 • 610.825.1524 • Fax: 610.825.2738  
**BIORIUS, RUE DE LA CROYERE 10A, BE-7170 MANAGE**

**NATURAL NAIL PREP**

1. Spray yours and your client's hands with *Purify* and gently massage. Push back cuticle and gently remove the shine with a *Endurance 180/240 Grit Buffer*. Using a *Nail Wipe* saturated with *Nailpure Plus*, press and rub into natural nail.
2. If extensions are desired, adhere tip or fit a nail form at this time.
3. Apply *Essential Bond* to the natural nail. Remove the brush from the bottle and wipe along the edge of the bottle, then brush onto two natural nails. Re-dip the brush and repeat the process until the nails are coated. Allow to dry for one minute. They will not appear chalky white.
4. Before you begin sculpting your enhancement, apply an even layer of *Essential Base Coat*, this thin layer will ensure that proper bonding and adhesion will occur for the subsequent layers. Cure in *Dual Cure* lamp, LED for 30 seconds or UV for 2 minutes.

**NATURAL NAIL OVERLAY OR TIP & OVERLAY**

1. Squeeze out and slice a small amount of the *Natural PolyPaste* and roll onto the natural nail near the cuticle area. (You can always add more product if needed.)
2. Dip the brush end of your *PolyPaste Tool* into *Cleanse* and dab off the excess liquid. Be sure to not wipe away too much of the *Cleanse* from the brush. *Cleanse* helps to move *PolyPaste*, and will keep it from sticking to the brush.
3. Allowing room for your margin at the cuticle, lightly pat and push *PolyPaste* into shape with the moist brush. Pull the *PolyPaste* forward towards the free edge. Be sure to cover the body of the nail with an even coverage. Keep the brush moist with *Cleanse* for ease of application, but do not over saturate the brush. Cure in *Dual Cure Lamp*, LED for 60 Seconds or 2 min in UV.
4. Do not remove the tacky dispersion layer. If another layer of *PolyPaste* is required, than repeat step 3. Check the nail from all angles to ensure proper apex placement. If necessary, add a small amount of a *PolyPaste* to the upper arch. This will ensure a strong nail and reinforce the structure of the enhancement. Cure in *Dual Cure Lamp*, LED for 60 Seconds or 2 min in UV. Wipe off the tacky dispersion layer using a *Nail Wipe* saturated with *Cleanse*.
5. Refine file using your *Endurance 180/180 Grit file*. Check for proper design and apex placement. File the nail so it is smooth, balanced and attractive following the curvature of the nail. Remove excess dust with your *Plush Brush*. Use a *Nail Wipe* saturated with *Cleanse* to remove any dust that may be hiding in the side walls.
6. Apply *Essential Seal* and cure in the *Dual Cure Lamp* for 30 sec or UV for 2 min. Wipe off the tacky dispersion layer using a *Nail Wipe* saturated with *Cleanse*. Condition the cuticle and surrounding skin with *Nurture Oil*.

**FRENCH SCULPTING ON A FORM**

1. After nail prep is done, apply your form to the natural nail. Squeeze out and slice a small amount of the *Natural PolyPaste* and roll onto the natural nail. (You can always add more product if needed.) Pull the *PolyPaste* forward towards the free edge. Be sure to cover the body of the nail with an even coverage and create a thin platform onto the *Platinum Nail Form*.
2. Lightly pat and push *PolyPaste* into shape with the moist brush. Pull the *PolyPaste* forward towards the free edge. Be sure to cover the body of the nail with an even coverage. Keep the brush moist with *Cleanse* for ease of application, but do not over saturate the brush. Cure in *Dual Cure Lamp*, LED for 60 Seconds or 2 min in UV.

3. Squeeze out and slice a small amount of the *Soft Pink PolyPaste* and roll onto the natural nail and the platform that you have created. Lightly pat and push *PolyPaste* into shape with the moist brush. Ensure that the body and smile line edges are neat and smooth for the white application to be applied up against. (You can always add more product if its needed.) Cure in *Dual Cure Lamp*, LED for 60 Seconds or 2 min in UV.
4. Squeeze out and slice a small amount of the *Soft White PolyPaste* and roll onto the edge of the free edge. Lightly pat and push *PolyPaste* into shape with the moist brush. Push up against the ledge you made with your pink *PolyPaste*. Cure in *Dual Cure Lamp*, LED for 60 Seconds or 2 min in UV.
5. Refine file using your *Endurance 180/180 Grit File*. Check for proper design and apex placement. File the nail so it is smooth, balanced and attractive following the curvature of the nail. Remove excess dust with your *Plush Brush*. Use a *Nail Wipe* saturated with *Cleanse* to remove any dust that may be hiding in the side walls.
6. Apply *Essential Seal* and cure in the *Dual Cure Lamp* for 30 sec or UV for 2 min. Wipe off the tacky dispersion layer using a *Nail Wipe* saturated with *Cleanse*. Condition the cuticle and surrounding skin with *Nurture Oil*.

**INFILLS**

**After Nail Prep**

1. Squeeze out and slice a small amount of the *PolyPaste* (colour of your choice) and roll onto the natural nail near the cuticle area. (You can always add more product if needed.)
2. Dip the brush end of your *PolyPaste Tool* into *Cleanse* and dab off the excess liquid. Be sure to not wipe away too much of the *Cleanse* from the brush. *Cleanse* helps to move *PolyPaste*, and will keep it from sticking to the brush.
3. Allowing room for your margin at the cuticle, lightly pat and push *PolyPaste* into shape with the moist brush. Pull the *PolyPaste* forward to blend into the original product. Continue to blend the new product into the original, and apply more product at the apex if required. Keep the brush moist with *Cleanse* for ease of application, but do not over saturate the brush. Cure in *Dual Cure Lamp*, LED for 60 Seconds or 2 min in UV.
4. Refine file using your *Endurance 180/180 Grit file*. Check for proper design and apex placement. File the nail so it is smooth, balanced and attractive following the curvature of the nail. Remove excess dust with your *Plush Brush*. Use a *Nail Wipe* saturated with *Cleanse* to remove any dust that may be hiding in the side walls.
5. Apply *Essential Seal* and cure in the *Dual Cure Lamp* for 30 sec or UV for 2 min. Wipe off the tacky dispersion layer using a *Nail Wipe* saturated with *Cleanse*. Condition the cuticle and surrounding skin with *Nurture Oil*.